

Fabric Seal C<sup>™</sup> Concentrate (FS-C) is a concentrated, water based fire retardant designed for treatment of fabrics. Fabric Seal C<sup>™</sup> is water borne mix of proprietary ingredients, which forms a carbon char when the treated fabric is exposed to fire. Once the carbon char is formed there will be minimal flame propagation, smoke evolution or afterglow. The product is designed for interior use only.

## **APPLICATION**

Fabric Seal C<sup>™</sup> is a highly concentrated version of the product, designed for shipping savings or commercial applications.

Most fabrics, when properly treated with the correct Fabric Seal dilution can pass the NFPA 701, FAR 25.853, British Standards 5852 (1,2), UFAC.

Fabric Seal™ Fire Retardants can be applied via Spray, Dipping or Machine application. The product must penetrate the fabric and be allowed to thoroughly dry to be effective. The recommended coverage rate is 300 ft² per gallon after proper dilution. Most fabrics properly treated with this product will meet the NFPA 701 requirements.

It is recommended that a small sample be tested for penetration and color fastness before application. Excess material should be removed by mechanical action (wringing or spin cycle). Then simply allow to air dry or force dry with a mechanical dryer.

This product may be used on: carpet, draperies, furniture, wall coverings, rayon, polyester, most synthetics and blends.

Fabric Seal™ Fire Retardants contain watersoluble ingredients that can be removed by exposure to significant amounts of water during cleaning. It is recommended that the fabric be re-treated with Fabric Seal™ after dry cleaning three times or one machine washing.

Note: Some stiffening of the treated fabrics may occur, especially with heavier treatments. It is the end users responsibility to find the optimal degree of fire retardancy vs. any stiffening for their application.

# PACKAGING & HANDLING

Fabric Seal  $C^{\mathbb{M}}$  is a liquid available in various packaging sizes from a 1 gallon pail to bulk containers.

Refer to SDS for proper handling.

# STORAGE CONDITIONS

- Temp: 40 90 °F
- Two year shelf life from manufacture date.

## **TYPICAL ANALYSIS**

Total Solids 31 - 34%

Weight per Gallon 9.9 - 10.2 lbs

Specific Gravity 1.19 - 1.23

ph **5.5 - 6.5** 

Product contains no PBDE's (Polybrominated Diphenyl Ethers) or petroleum derivatives.

## **WARRANTIES**

Products are guaranteed to perform their fire retardant function as represented by third party tests, if applied according to manufacturer's published instructions.

\*There are no other warrantees either expressed or implied since Flame Seal Products cannot control the actual application of the products. Users must determine usability and suitability for their particular requirements, as well as compatibility with the exact materials to be treated or coated.

FLAME SEAL PRODUCTS, INC.

9420 Knight Road Houston, TX, 77045 USA 713-668-4291 (office) 713-668-1724 (fax) www.flameseal.com